

Cobalt Anodes

Electrolytic Cobalt Anodes

Gilbert & Jones electrolytic cobalt is recommended for all high purity plating and alloying applications. Certificates of analysis are available for all shipments.

Gilbert & Jones service and dependability are well known and firmly established in the marketplace. All cobalt anode sales are supported by an experienced, technically astute sales staff, capable of providing technical assistance in the evaluation of customer plating issues.



Available Forms

Gilbert & Jones electrolytic cobalt anodes are available in cracked cathode form.

Typical Analysis

Cobalt	> 99.950	%
Carbon	< 0.0015	%
Copper	< 0.0003	%
Hydrogen	< 0.0002	%
Iron	< 0.0010	%
Lead	< 0.0002	%
Nickel	< 0.0300	%
Nitrogen	< 0.0003	%
Oxygen	< 0.0040	%
Sulfur	< 0.0002	%
Zinc	< 0.0001	%

Material Safety Data Sheet available on request.
C of A available with all shipments.



Gilbert & Jones Company, Inc.

35 Peter Court, New Britain CT, 06051 • 1-800-577-2962

www.gilbertandjones.net